

**ADHESIVE TAPE**

**Patent number:** JP10121000  
**Publication date:** 1998-05-12  
**Inventor:** UEKI ETSUO; KAMETANI HIDEYUKI; ISHIKO HIROTO;  
SHIBATA HIKARI  
**Applicant:** DIATEX KK; HARIMA CHEMICALS INC  
**Classification:**  
**- International:** C09J7/02; C09J7/04; C09J133/06; C09J7/02;  
C09J7/04; C09J133/06; (IPC1-7): C09J7/02; C09J7/04;  
C09J133/06  
**- european:**  
**Application number:** JP19960298114 19961021  
**Priority number(s):** JP19960298114 19961021

Report a data error here

**Abstract of JP10121000**

**PROBLEM TO BE SOLVED:** To obtain an excellent adhesive tape having good tearability with hands and high adhesive force, capable of being easily be peeled on a peeling operation after an ageing treatment, not leaving on an adherend, having excellent repeelability, not discolored with time and useful for ageing building materials. **SOLUTION:** This adhesive tape is produced by forming an adhesive layer on one side of a thermoplastic resin substrate, and has good tearability. Therein, the adhesive tape has a tear strength of 0.2-1.0kgf, and the adhesive agent comprises an adhesive composition produced by crosslinking the mixture of 100 pts.wt. (as solid content) of an acrylic copolymer with 3-30 pts.wt. of a petroleum and/or terpene tackifier resin having a softening point of 70-150 deg.C by the use of 0.01-2 pts.wt. of a metal compound. The acrylic copolymer comprises an alkyl (meth)acrylate ester and its copolymerizable vinylic monomer, has a weight-average mol.wt. of 300,000-1,000,000 and a dispersion degree of 6-12.

---

Data supplied from the **esp@cenet** database - Worldwide